

### Product description

Rockwool Marine Firebatts 110 is a semi-rigid slab made of stone wool.

#### Application

Marine Firebatts 110 is primarily used as high temperature insulation. Furthermore the products can be used as insulation of structures where the temperature exceeds 250°C.




### Technical properties

Parameter	Value	Standard
<b>Thermal conductivity</b>	$\lambda_{10} = 0,035 \text{ W/mK}$ $\lambda_{100} = 0,045 \text{ W/mK}$ $\lambda_{300} = 0,084 \text{ W/mK}$	EN 12667
<b>Nominal density</b>	110 kg/m <sup>3</sup>	-
<b>Compressive strength</b>	-	EN 826
<b>Fire classification</b>	Non-combustible	IMO A.799(19)
<b>Water absorption (short term)</b>	<1 kg/m <sup>2</sup>	EN 1609
<b>Max. service temp.</b>	Wool: 750°C	-
<b>Sound absorption directly mounted</b>	-	ISO 354 (approximated) Evaluated after ISO 11 654
<b>Facings</b>	-	IMO A.653(16) (low flame - spread)
<b>Dimensions</b>	Marine Firebatts 110: L: 1000 mm - W: 600 mm - T: 25,50 mm	



Rockwool A/S  
 DK-2640 Hedehusene  
 Tel.: +45 46 56 16 16  
 Fax: +45 46 56 16 04  
 E-mail: [export@rockwool.dk](mailto:export@rockwool.dk)  
 Internet: [www.rockwool-marine.com](http://www.rockwool-marine.com)

Rockwool Marine & Offshore:  
 Hong Kong Office  
 Suite 1303, Asia Orient Tower, Town Place  
 33 Lockhart Road, Wanchai, Hong Kong  
 Tel: +852 2866 6180  
 Fax: +852 2866 9555



Rockwool A/S reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.