

**Rockwool Product  
Information****Product Data Sheet 2.40**  
**Comfort Batt 45/60/80 2.40.3****INTRODUCTION**

ROCKWOOL COMFORT BATT 45/60/80 are batts of non-combustible mineral wool specially suited for comfort insulation.

The lightweight of Rockwool Comfort Batt makes them ideal for situations where reduction in weight is important.

The most common application for Rockwool Comfort Batt is thermal- and sound insulation in industry, ships and offshore constructions.

**ADVANTAGES**

- Excellent thermal- and acoustic insulation
- Non-combustible
- Strong and flexible
- Chemically inert
- Vermin and rot proof
- Resists high temperatures
- Easy to cut and handle
- Cost effective
- Maintenance free

**DIMENSIONS**

L x W 900 x 600 mm  
Thickness 30 - 150 mm

Other dimensions can be supplied on request.

**NOMINAL DENSITY**

ROCKWOOL COMFORT BATT 45: 45 kg/m<sup>3</sup>  
ROCKWOOL COMFORT BATT 60: 60 kg/m<sup>3</sup>  
ROCKWOOL COMFORT BATT 80: 80 kg/m<sup>3</sup>

**FACING**

ROCKWOOL COMFORT BATT 60/80 can be supplied with a reinforced aluminium foil on one side.

**PACKING**

Shrink-wrapped in PE-foil.

**THERMAL CONDUCTIVITY ( $\lambda$ -value)**

ROCKWOOL COMFORT BATT 45:  $\lambda_{10} = 0,035$  W/mK  
ROCKWOOL COMFORT BATT 60:  $\lambda_{10} = 0,034$  W/mK  
ROCKWOOL COMFORT BATT 80:  $\lambda_{10} = 0,036$  W/mK

**SERVICE TEMPERATURES**

Comfort Batt can be used in continuous service at temperatures up to 250 ° C.

The stone fibres in Rockwool mineral wool have a high natural resistance to fire and can withstand temperatures of more than 1000 ° C without melting.

**FIRE**

Rockwool Comfort Batt is classified as non-combustible when tested according to ISO 1182 and IMO Res. A 799(19).

**WATER**

Impregnated Rockwool mineral wool is water-repellent, and absorbs water only when the latter is pressed or forced into the product.

Rockwool mineral wool will absorb only approx. 1 % of its volume in moisture when tested according to BS 2972:75.

The hygroscopic water content in Rockwool mineral wool is only approx. 0,004 % per volume at RH 95%.

Diffusion rating is approx. 0,14 kg/m.s.GPa.

**CORROSION**

Since Rockwool mineral wool is made of practically non-alkaline materials, it does not react chemically and consequently does not promote corrosion.

**ENVIRONMENT**

No CFSs or HCFCs are used in the manufacturing of Rockwool products.

**QUALITY ASSURANCE**

A/S Rockwool have a well established and operating quality control system, and the system has been certified to meet the requirements in NS-ISO 9001.

**A/S ROCKWOOL**

reserves at all times the right to alter the product specifications of the products without notice due to process improvements. The technical information is therefore to be used only as a guide.

A/S Rockwool  
P.O.Box 4215 Nydalen  
N-0401 Oslo  
Norway

Telephone: + 47 22 02 40 00  
Telefax: + 47 22 15 91 78  
E-mail: [rockwool@rockwool.no](mailto:rockwool@rockwool.no)  
Internet: [www.rockwool.no](http://www.rockwool.no)